











FireWarrior®
No burns at all

by: **EyeveX**
Our vision. Your safety.

INHERENT FR COVERALL

55% Modacrylic 43% Cotton 2% Antistatic

Model: FW 18555432 IFR

FABRIC	WEIGHT	CERTIFICATION FULFILMENTS		CARE INSTRUCTIONS
Modacrylic cotton 185	185 ± 5% g/m ²	EN 1149-3 ISO 14116 3/50I/75 EN ISO A1 B1 C1 F1 IEC 61482-2-1, 4kA ASTM 1959 (HRC1)	   	   

STYLE & DESIGN

- 8 Pockets Design
 - Two chest pockets, one with flap & pencil slot on the left/ two side pockets
 - Two rear pockets, one with flap on the right/ One tool pocket in the right leg
- With "pass through" to access the inner garment
- Two way heavy duty metallic zipper, snap button and storm flap closure
- Fully double stitched and bar tacked stress points
- Action back allowing maximum body movement
- Full sleeves with adjustable cuffs
- Permanent sewn crease line
- Snap button neck closure
- With hanging hook on collar
- Concealed elastic waist on backside



Mfg for and marketed by
EyeveX Safety U.S.A., Inc.
1013 Centre Road, Suite 403-B, Wilmington, DE 19805, U.S.A.
www.eyevexsafety.com
Made in India

INHERENTLY SAFE: PERMANENT PROTECTION FOR THE WEARER



**HEAT AND FLAME RESISTANT
ALUMINIUM SPLASH PROTECTION, STATIC
CONTROL & ELECTRIC ARC PROTECTION AND
WELDING**



**VERY RESILIENT AND
DURABLE**



**HIGH VISIBILITY YELLOW
AND CHEMICAL SPLASH
OPTIONS AVAILABLE**



INDUSTRIALLY LAUNDERABLE



EXTREMELY COMFORTABLE



FABRIC DESCRIPTION

Fibre Blend	55% Modacrylic, 43% Cotton, 2% Antistatic
Weight	185 ± 5% g/m
Yarn Count	240 x 240
Construction	EPI 96 PPI 56, ASTM D 3775-03a
Weave	2/1 LHT
Full Width	150 cm
Tensile Strength (N)	Warp min 300 Weft min 280, ISO 13934-3 Strip Method
Tear Strength (N)	Warp 10 Weft 10, ISO 13937-2 Trouser Shape
% Shrinkage (After 5HL)	Warp ±, Weft ±3, ISO 6330:2000-2A Temp 60°C
Seam Sippage (N)	Warp > 100 Weft > 100 ISO 13936-1





FireWarrior®
No burns at all

by: **EyeveX**
Our vision. Your safety.

Colour Fastness	
To washing	3-4 ISO 105 C-06
Colour Change	4
To water	3-4 ISO 105 E-10
To crocking	Dry 4 Wet 3 , ISO 105 X-12
Notes: Colour performance results shown are average value. Dark and special colours may not meet figured quoted	

pH	
Value	6-8, ISO 3071

Other Performances	
Antistatic Behaviour	EN 1149-3
Flame Resistance	ISO 14116 3/50I/75
Heat & Flame Resistance	EN ISO 11612 A1 B1 C1 F1
Electric Arc	IEC 61482-2-1, 4kA
Electric Arc	ASTM 1959 (HRC1)

Wash Care Instructions
   



Mfg for and marketed by
EyeveX Safety U.S.A., Inc.
1013 Centre Road, Suite 403-B, Wilmington, DE 19805, U.S.A.
www.eyevexsafety.com
Made in India